What is claimed is:

1. A tarpaulin comprising:

a polypropylene woven fabric layer prepared by weaving polypropylene multifilament yarn; and

a resin composition layer which is press-coated on either or both sides of said polypropylene woven fabric layer, wherein the resin composition is obtained by melt-kneading ethylene-propylene copolymer and ethylene-octene random copolymer or styrene-ethylene-butene block copolymer.

2. The tarpaulin according to claim 1, wherein said resin composition layer is obtained by melt-kneading 60 ~ 95 parts by weight of ethylen-propylene copolymer and 5 ~ 40 parts by weight of ethylene-octene random copolymer or styrene-ethylene-butene block copolymer.

3. The tarpaulin according to claim 1 or claim 2, wherein said ethylene-propylene copolymer satisfies the following condition:

1) ethylene content : 20 ~ 30 mole%;

2) melt index : 15 ~ 30 g/10 minutes

3) density : 0.890 ~ 0.900 g/cm^3.

4. The tarpaulin according to claim 1 or claim 2, wherein said ethylene-octene random copolymer satisfies the following condition:

1) ethylene content : 60 ~ 90 parts by weight;

2) octene content : 40 ~ 10 parts by weight

3) pattern viscosity : 1.5 ~ 10 at ML 1+4 (121°C)

5. The tarpaulin according to claim 1 or claim 2, wherein said styrene-ethylene-butene block copolymer satisfies the following condition:

1) pattern viscosity : 1.0 ~ 18 at ML 1+4 (121°C)

6. The tarpaulin according to claim 1, wherein the tensile strength of said multifilament yarn is 6.5 ~ 7 g/D.

7. A process for preparing a tarpaulin, comprising the steps of:

1) preparing polypropylene woven fabric by weaving polypropylene multifilament yarn; and

2) applying a resin composition obtained by melt-kneading ethylene-propylene copolymer and ethylene-octene random copolymer or styrene-ethylene-butene copolymer on either or both sides of said polypropylene woven fabric and extruding by an extruder.